


EZ-Bend® Single-Mode Optical Fiber

The Industry's Best Macrobend Performance in a Solid-Core G.652.D-Compatible Fiber



Applications

EZ-Bend Fiber provides outstanding bend performance and design freedom for fiber management systems in:

- FTTH – Multi-dwelling Units (MDUs), in-building applications and drop cables
- Central office
- High power applications
- Closures
- At the customer premises

Outstanding Macrobend Performance

- **1 turn on a 5 mm radius mandrel**
≤ 0.10 dB at 1550 nm
≤ 0.20 dB at 1625 nm
- **1 turn on a 2.5 mm radius mandrel**
≤ 0.20 dB at 1550 nm
≤ 0.30 dB at 1625 nm

Features and Benefits

- Full spectrum fiber provides a 40% increase in usable optical spectrum ready for XG-PON and NG-PON2
- Fully compliant with the ITU-T G.657.B3 recommendation; also compatible with ITU-T G.652.D
- The only G.657.B3 solid glass fiber designed to reliably support low loss even with 2.5 mm radius bends
- Tight geometry for low splice loss and improved connectorization performance
- Excellent fusion splice performance

Overview

EZ-Bend Single-Mode Optical Fiber offers outstanding bend performance to a 2.5 mm radius for the most challenging in-residence and MDU applications. The fiber, developed using OFS' groundbreaking EZ-Bend Optical Technology, provides at least three times' lower loss at tight bends than comparable products. Compatible with the installed base of conventional G.652.D single-mode fibers, the fiber meets and exceeds ITU-T G.657.B3 recommendations.

Product Description

Cables using EZ-Bend Optical Fiber can be routed around corners and deployed using traditional fast and easy copper wire installation processes with negligible signal loss. Ideal for aggressive routing environment where space is at a premium, EZ-Bend Fiber offers reliable support for MDU and in-home wiring applications.

EZ-Bend Fiber features solid synthetic glass construction that enables uniform macrobending loss axially and in all bending planes. This results in easy splicing to G.652.D fibers with existing core and clad alignment splicers and standard termination using conventional optical connectors and polishing techniques.

EZ-Bend Fiber retains full spectrum performance due to OFS' patented fiber manufacturing process, which eliminates hydrogen-aging defects. Its ultra-low fiber Polarization Mode Dispersion (PMD) enables speed and distance upgrades.

EZ-Bend® Single-Mode Optical Fiber

For additional information please contact your sales representative.

You can also visit our website at www.ofsoptics.com or call **1-888-fiberhelp** (1-888-342-3743) USA or **1-770-798-5555** outside the USA.

North America

Telephone: 508-347-8590
Toll Free: 800-799-7732
Fax: 508-347-1211
E-mail: fibersalesnar@ofsoptics.com

Asia Pacific

Telephone: +852 2506 5054
Fax: +852 2506 0166
E-mail: fibersalesap@ofsoptics.com

Caribbean, Latin America

Telephone: +1-508-347-8590
Fax: +1-508-347-1211
E-mail: fibersalescala@ofsoptics.com

Japan

Telephone: +81-3-3286-3424
Fax: +81-3-3286-3708 or 3190
E-mail: fibersalesjapan@ofsoptics.com

Europe, Middle East, Africa

Telephone: +45-43 48 3736
Fax: +45 4348 3444
E-mail: ofssalesdk@ofsoptics.com

China

Telephone: +86 10 6505 3660
Fax: +86 10 65059515
E-mail: fibersaleschina@ofsoptics.com



Copyright © 2018 OFS Fitel, LLC.
All rights reserved, printed in USA.

OFS Marketing Communications
Doc ID: fiber-155
Date: 0118

EZ-Bend is a registered trademark of OFS Fitel, LLC.

OFS reserves the right to make changes to the prices and product(s) described in this document at any time without notice. This document is for informational purposes only and is not intended to modify or supplement any OFS warranties or specifications relating to any of its products or services.

Product Specifications		EZ-Bend Single-Mode Optical Fiber	
Physical Characteristics			
Clad Diameter	125.0 ± 0.7 μm		
Clad Non-Circularity	≤ 0.7 %		
Core/Clad Concentricity Error (Offset)	≤ 0.5 μm, < 0.2 μm typically		
Coating Diameter (Uncolored)	237 - 247 μm		
Coating-Clad Concentricity Error (Offset)	≤ 12 μm		
Tensile Proof Test	100 kpsi (0.69 GPa)		
Coating Strip Force	Range: 1.0 N ≤ CSF ≤ 8.9 N		
Standard Reel Lengths	up to 32 km		
Optical Characteristics			
Attenuation	Maximum		
at 1310 nm	≤ 0.35 dB/km		
at 1383 nm ¹	≤ 0.35 dB/km		
at 1490 nm	≤ 0.24 dB/km		
at 1550 nm	≤ 0.21 dB/km		
at 1625 nm	≤ 0.23 dB/km		
¹ After H2 aging tests according to IEC 60793-2-50			
Attenuation vs. Wavelength ²	Reference (nm) λ	α	
Range (nm)			
1285 – 1330	1310	0.03	
1360 – 1480	1385	0.04	
1525 – 1575	1550	0.02	
1460 – 1625	1550	0.04	
*The attenuation in a given wavelength range does not exceed the attenuation of the reference wavelength (λ) by more than the value α.			
Attenuation Uniformity / Point Discontinuities at 1310 nm and 1550 nm	≤ 0.05 dB		
Chromatic Dispersion			
Zero Dispersion Wavelength (λ ₀)	1250 – 1324 nm		
Zero Dispersion Slope (S ₀)	≤ 0.11 ps/nm ² -km		
Cut-off Wavelength (λ _{cc})	≤ 1260 nm		
Group Refractive Index			
at 1310 nm	1.467		
at 1550 nm	1.468		
Mode Field Diameter			
at 1310 nm	8.3 – 9.1 μm		
at 1550 nm	9.2 – 10.4 μm		
Polarization Mode Dispersion (PMD) ¹			
Fiber PMD Link Design Value (LDV) ²	≤ 0.06 ps/√km		
Maximum Individual Fiber	≤ 0.1 ps/√km		
¹ As measured with low mode coupling (LMC) technique in fiber form, value may change when cabled. Check with your cable manufacturer for specific PMD limits in cable form.			
² The PMD Link Design Value complies with IEC 60794-3, September 2001 (N = 20, Q = 0.01%). Details are described in IEC 61282-3 TR Ed 2, October 2006.			
Environmental Characteristics (at 1310, 1550 & 1625 nm)			
Temperature Cycling (-60° + 85 °C)	≤ 0.05 dB/km		
High Temperature Aging (85 ± 2 °C)	≤ 0.05 dB/km		
Water Immersion (23 ± 2 °C)	≤ 0.05 dB/km		